



**Distributions Fillion Marquis International Itée**  
420 Industriel Blvd., local 100, Saint-Jean-sur-Richelieu, QC J3B 4S6  
Tel.: 450-349-2226 • Fax: 450-349-1799 • Toll free: 1-877-989-2226  
[passeportelite.com](http://passeportelite.com)

**TECHNICAL DATA SHEET**  
**INDUSTRIAL POLYASPARTIC**  
**98.5% SOLIDS**  
**PE700235**

**DESCRIPTION**

Passeport Élite Industrial Polyaspartic PE700235 is a two-component, 98.5% solids, VOC compliant, long working time aliphatic polyurea, developed for UV stable floor topcoats. It provides outstanding appearance, superior chemical, UV, and solvent resistance. It exhibits excellent physical properties. This system complies with the Canadian Food Inspection Agency (CFIA).

**PRIMARY APPLICATIONS**

- Marine protection for fiberglass, steel, concrete or wood
- UV-stable topcoat
- Aircraft hangar floors
- Low temperature equipment
- Maintenance facilities
- Offshore platforms
- Industrial shop floors
- Car washes or wash bays
- Secondary Containment
- Cooling towers
- Bridges
- Wastewater treatment applications

**ADVANTAGES**

- Long pot life (40-50 minutes @ 25°C)
- Displays fast cure times with excellent adhesion
- Superior chemical resistance
- Superior weather and abrasion resistance
- Non yellowing and good gloss retention
- Easy to mix 1:1 ratio by volume
- Emits virtually no odours and can be applied indoors
- Excellent adhesive properties, allowing application on other firm and hard coating, as well as a good bond to the substrate
- VOC compliant in all 50 states and Canada

**TECHNICAL DATA**

<b>Packaging</b>	7,57 L (2 gal US)	
<b>Colour</b>	Upon Request	
<b>Yield/Recommended Thickness</b>	Primer	5-10 mils
	Finish Coat	6-10 mils
<b>Shelf Life</b>	12 months in original unopened factory sealed containers. Keep away from extreme cold, heat, or moisture. Keep out of direct sunlight and away from fire hazards.	
<b>Mix Ratio, by volume</b>	A: B = 1:1 (100:100)	
<b>Mix Ratio, by weight (grams)</b>	A: B = 100:107	
<b>Pot Life (454g)</b>	40-50 minutes @ 25°C	

**PROPERTIES @ 23°C (73°F) and 50% R.H.**

PASSEPORT

# ELITE

Distributions Fillion Marquis International Itée

420 Industriel Blvd., local 100, Saint-Jean-sur-Richelieu, QC J3B 4S6

Tel.: 450-349-2226 • Fax: 450-349-1799 • Toll free: 1-877-989-2226

[passeportelite.com](http://passeportelite.com)

**TECHNICAL DATA SHEET**  
**INDUSTRIAL POLYASPARTIC**  
**98.5% SOLIDS**  
**PE700235**

<b>Solids Content, by weight</b>	<b>Part A</b>	<b>Part B</b>	<b>Mix</b>
	100%	100%	98,50%
<b>Solids Content, by volume</b>	<b>Part A</b>	<b>Part B</b>	<b>Mix</b>
	100%	100%	98,50%
<b>Specific gravity</b>	<b>Part A</b>	<b>Part B</b>	<b>Mix</b>
	1.12 - 1.13	1.12 - 1.13	1.05 - 1.10
<b>Thinner Recommended</b>	Xylene		
<b>Working Time (25°C / 40% R.H.)</b>	35-45 minutes		
<b>Abrasion Resistance, ASTM D4060, Taber Abrader CS-17 Wheel / 1000g (2.2 lbs.) / 1000 cycles</b>	30 mg loss		
<b>Adhesion, ASTM D4541</b> Concrete-primer	> 500 psi (ruptures de substrat)		
<b>Water Absorption, ASTM D570</b>	0,2%		
<b>Water Vapour Transmission, ASTM E96</b> Water Procedure B Film 0.01cm (0.004")	1 perm		
<b>Hardness (Shore D), ASTM D2240</b>	75-78		
<b>Flexibility, 1/8" Mandrel, ASTM D1737</b>	Réussi		
<b>Falling Sand Abrasion Resistance (L sand/ 1 dry mil), ASTM D968</b>	45		
<b>Viscosity @ 25°C</b>	<b>Part A</b>	<b>Part B</b>	<b>Mix</b>
Clear	400-500	150-180	300-40
<b>Recoat</b>	Substrate Temperature		Minimum
	± 10 °C / 50°F		1 day
	± 20 °C / 68°F		6 hours
± 30 °C / 86°F		4 hours	8 hours
<b>Curing Details</b>	Substrate Temp.	Foot Traffic	Light Traffic
	± 10 °C	3 days	7 days
	± 20 °C	2 days	5 days
	± 30 °C	1 day	3 days
<b>Gloss, ASTM D523</b>	95+		
<b>Fire Rating CAN/ULC S102</b>	Estimated on similar coating		
	Flame spread 5		
	Smoke developed 94		
<b>Tensile Strength, ASTM D638</b>	7000-8000 psi		

**TECHNICAL DATA SHEET**  
**INDUSTRIAL POLYASPARTIC**  
 98.5% SOLIDS  
 PE700235

<b>Compressive Strength (psi MPa), ASTM D695</b>	9000-10000
	*W/Quartz 13700
	*W/Chips 12200
<b>Elongation at Break, ASTM D638</b>	100-110%
<b>Tear Strength (PLI), ASTM D2240</b>	350
<b>VOC</b>	0 g/L

**\*Please note, that the indicated mileage is calculated for flat surfaces. A porous or imperfect surface will require more material in order to cover the same surface area.\***

**\*\*Please note that the indicated viscosity is for clear product only. Any addition of colourant may affect the viscosity.\*\***

**SURFACE PREPARATION**

**Old concrete**

Concrete surface must be cleaned and mechanically prepared using shotblasting, sand blasting, and/or diamond grinding. All oils, sealers, curing agents, waxes and fats must be removed prior to product application. Do not apply onto wet substrates. Chloride, moisture, and pH levels should be checked prior to application. All cracks and substrate imperfections should be filled and repaired prior to application.

**New concrete**

New concrete should be allowed to cure for a minimum of 30 days. Compression resistance of concrete must be at least 25 MPa (3625 lbs./inch<sup>2</sup>) after 28 days and traction resistance must be at least 1,5 MPa (218 lbs./inch<sup>2</sup>). Shotblasting, sand blasting, and/or diamond grinding is required to remove the surface laitance that appears during the concrete finishing and curing process. A primer (Passeport Élite Industrial Epoxy PE700231) is recommended to be used to seal porous concrete surfaces prior to application. All cracks and substrate imperfections should be filled and repaired prior to application.

**MIXING**

Materials should be pre-conditioned to at least 15°C (50°F) prior to use. Pour component B into component A in the appropriate mixing ratio: 1A:1B by volume. Mix thoroughly by hand with a stirring paddle for 1 minute, taking care to mix the center as well as the side of the product. Only prepare quantity that may be applied during pot life of mixture.

**APPLICATION**

Apply mixed product on the prepared surface tightly (thin film) using a rubber rake and pass a roller to obtain a uniform coating. Avoid creating puddles.



**Distributions Fillion Marquis International Itée**  
420 Industriel Blvd., local 100, Saint-Jean-sur-Richelieu, QC J3B 4S6  
Tel.: 450-349-2226 • Fax: 450-349-1799 • Toll free: 1-877-989-2226  
[passeportelite.com](http://passeportelite.com)

**TECHNICAL DATA SHEET**  
**INDUSTRIAL POLYASPARTIC**  
**98.5% SOLIDS**  
**PE700235**

**CLEANING**

Clean all application equipment with a specified cleaner. Once the material hardens it can only be removed mechanically. If the product splatters, wash thoroughly with hot soapy water.

**OVERLAPS**

**Primer:** Subsequent overlaps must be applied when primer is still wet or tacky. If primer has dried, reprime. Porous substrates may require multiple priming.

**Finish Coat:** Subsequent overlaps must be applied when finish coat is still wet or tacky. If it has dried, recoat.

**RESTRICTIONS**

- Minimum/Maximum temperature of substrate: 15°C / 30°C (59°F / 86°F).
- Maximum relative humidity during application and curing: 85%.
- Humidity content of substrate must be < 4% when coating is applied.
- Do not apply on porous surfaces where a transfer of humidity may occur during application.
- Protect from humidity, condensation and contact with water during the 24-hour initial curing period.

**HEALTH AND SAFETY**

In case of skin contact, wash with water and soap. In case of eye contact, immediately rinse with water for at least 15 minutes. Consult a physician. For respiratory irritation, move affected person to fresh air. Remove contaminated clothes and clean before reuse.

Components A and B contain toxic ingredients. Prolonged contact of this product with the skin is susceptible to provoke an irritation. Avoid eye contact. Contact with product may cause serious burns. Avoid breathing vapors release from this product. This product is a strong sensitizer. Wear safety glasses and chemical resistant gloves. A breathing apparatus filtering organic vapors approved by the NIOSH/ MSHA is recommended. Work in well ventilated area.

**\*Consult the material safety data sheet for further information.\***

---

**IMPORTANT NOTICE**

All statements, recommendations and technical information contained in this document are accurate to the best knowledge of Passeport Élite. The data relates only to the specific material designated herein. It may not be valid if used in combination with any other materials. It is the users' responsibility to verify suitability of this information for their own particular use, and to test this product before use. Passeport Élite assumes no legal responsibility for use upon these data. Passeport Élite assumes no legal responsibility for any direct, indirect, consequential, economic, or any other damage except to replace the product or refund the purchase price as set out in the purchase agreement.

**TECHNICAL DATA SHEET**  
**INDUSTRIAL POLYASPARTIC**  
**98.5% SOLIDS**  
**PE700235**

**CHEMICAL RESISTANCE**

Chemical	Results (25°C)
Acetic Acid 100%	C
Acetone	C
Ammonium Hydroxide 50%	RC
Benzene	C
Brine Saturated H <sup>2</sup> O	R
Chlorinated H <sup>2</sup> O	R
Clorox (10%) H <sup>2</sup> O	R
Diesel Fuel	RC
Gasoline	RC
Gasoline/5% MTBE	RC
Gasoline/5% Methanol	RC
Hydrochloric Acid 20%	R
Hydrochloric Acid 10%	NR
Hydraulic Fluid (oil)	RC
Isopropyl Alcohol	R
Lactic Acid	RC
MEK	RC
Methanol	R
Methylene Chloride	C
Mineral Spirits	RC
Motor Oil	R
MTBE	C
Muriatic Acid 10%	R
NaCl/H <sup>2</sup> O 10%	R
Nitric Acid 20%	NR
Phosphoric Acid 10%	R
Phosphoric Acid 50%	NR
Potassium Hydroxide 10%	R
Potassium Hydroxide 20%	R, D
Propylene Carbonate	RC
Skydrol	C
Sodium Hydroxide 25%	R
Sodium Hydroxide 50%	R, D
Sodium Hypochlorite 10%	R
Sodium Bicarbonate	R
Stearic Acid	R
Sugar/H <sup>2</sup> O	R
Sulfuric Acid 10%	R
Sulfuric Acid >50%	RC
Toluene	R
1,1,1-Trichloroethane	C
Trisodium Phosphate	R
Vinegar/H <sup>2</sup> O 5%	R
H <sup>2</sup> O	R
H <sup>2</sup> O 14 days at 82°C	R
Xylene	RC

**R = Recommended – Little or no visible damage**

**RC = Recommended Conditional – Some effect, swelling or discolouration**

**C = Conditional – Cracking; wash within one hour of spillage to avoid affects**

**NR = Not Recommended**

**D = Discolouration**