

Distributions Fillion Marquis International Itée 420 Industriel Blvd., local 100, Saint-Jean-sur-Richelieu, QC J3B 4S6 Tel.: 450-349-2226 • Fax: 450-349-1799 • Toll free: 1-877-989-2226

www.passeportelite.com

TECHNICAL SHEET A.T. CATALYST PE700469

DESCRIPTION

Passeport Élite A.T. Catalyst is an aziridine crosslinker ideal to be used with water-based urethane varnishes. It provides enhanced:

- water and chemical resistance;
- adhesion to specific substrates;
- abrasion and mar resistance.

APPLICATION

- 1. It is recommended to use the catalyst only at the final coat of varnish.
- 2. Stir the varnish well before adding catalyst.
- 3. A.T. Catalyst has to be added slowly to the varnish under good stirring.
- 4. Let sit for 5 to 10 minutes before applying.
- 5. The mix should be used within 24 hours after preparation. After this time, it can be used as a first coat on another job.

For a safe and correct use, read Material Safety Data Sheet before handling the product.

NOTE

To the best of our knowledge, the information contained herein is accurate. Since conditions and methods are beyond our control, no warranty is expressed or implied as for the final result. The user is advised to access the suitability of the product on a test area before application.





Distributions Fillion Marquis International Itée 420 Industriel Blvd., local 100, Saint-Jean-sur-Richelieu, QC J3B 4S6 Tel.: 450-349-2226 • Fax: 450-349-1799 • Toll free: 1-877-989-2226

www.passeportelite.com

TECHNICAL SHEET A.T. CATALYST PE700469

PRODUCT SPECIFICATIONS

Dosage

15 ml (1/2 oz.) of A.T. Catalyst per liter (32 oz.) of finish (pot life: 24 hours once catalysed)

Clean up

Clean tools with water.

Storage

Store in a cool, dry, dark place. If stored under conditions of excessive heat for extended periods, the material may discolor, deteriorate, and even gel. KEEP OUT OF REACH OF CHILDREN.

Shelf life

At least 1 year in a well closed container.

Product specifications

Solids	$70 \pm 1\%$ (by weight); $67 \pm 1\%$ (by volume)
Density	1.01-1.02 kg/L
VOC	305 g/L

