

Distributions Fillion Marquis International Itée 420 Industriel Blvd., local 100, Saint-Jean-sur-Richelieu, QC J3B 4S6 Tel.: 450-349-2226 • Fax: 450-349-1799 • Toll free: 1-877-989-2226

www.passeportelite.com

TECHNICAL SHEET ANTI-SLIP COATING PE700490 • PE700491

DESCRIPTION

Colour: Tintable white (PE700490) Accent base (PE700491) Packaging: 3.78 L

The **Passeport Élite Anti-Slip Coating** makes concrete, asphalt and primed wood surfaces safer while enhancing their appearance. This textured coating is 100% acrylic and ideal for use anywhere an extremely durable, anti-slip finish is desired.

USAGE

Interior or exterior use on new or old concrete, asphalt or wood surfaces that have been properly prepared, such as parking lots, stairs, access ramps, walkways, sidewalks, playgrounds, patios, decks, pool decks, parks, tennis courts, etc.

SURFACE PREPARATION

New asphalt and new concrete surfaces must cure for at least 28 days prior to applying Passeport Élite Anti-Slip Coating. The surface to be coated should be well drained, free of cracks, clean and free of all loose dirt, debris, grease and oil. Cracks and surface defects should be filled with an appropriate specific use product.

Wood: Apply an appropriate primer before using Passeport Élite Anti-Slip Coating.

APPLICATION

Passeport Élite Anti-Slip Coating is best applied by pouring from container in an "S" pattern and then spreading with a squeegee or 18" roller. Apply liberally.

Architectural specifications

Apply 2 coats on properly prepared ashphalt, concrete or wood.

RESTRICTIONS

- Do not apply when air and surface temperature are below 10°C (50°F).
- Do not apply when rain is imminent.
- Do not apply when surface is above 60°C (140°F).
- Do not apply over tar emulsions less than 4 years old.
- Do not allow traffic over surface for at least 24 hours (or 48 hours in humid conditions).
- Pool decks must be clean and dry.
- Do not put in service until 24 hours after the last coat.

1/3

TECHNICAL SHEET ANTI-SLIP COATING PE700490 • PE700491



Distributions Fillion Marquis International Itée 420 Industriel Blvd., local 100, Saint-Jean-sur-Richelieu, QC J3B 4S6 Tel.: 450-349-2226 • Fax: 450-349-1799 • Toll free: 1-877-989-2226

www.passeportelite.com

TECHNICAL SHEET ANTI-SLIP COATING PE700490 • PE700491

SAFETY INFORMATION


CAUTION! KEEP OUT OF REACH OF CHILDREN.

Do not take internally. Close container after each use. This product contains more than 0.1% crystalline silica (CAS No. 14808-60-7) which has been classified by IARC as a Class 1 carcinogen. Normal application procedures pose no hazard since the silica is wet and encapsulated, but grinding or sanding dried films may yield respirable silica dusts. Control exposures to less than 0.1 mg/m³ using NIOSH-approved dust filter respirators.

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting Health Canada at 1-866-225-0709 or log onto www.hc-sc.gc.ca.

Some paint products may contain chemicals which are harmful if they come in contact with exposed skin. Protection for exposed skin (gloves, protective creams) should be available, and used per product directions.

NOTE: All floor coatings are more slippery when the surface becomes wet or contaminated with debris.





Distributions Fillion Marquis International Itée 420 Industriel Blvd., local 100, Saint-Jean-sur-Richelieu, QC J3B 4S6 Tel.: 450-349-2226 • Fax: 450-349-1799 • Toll free: 1-877-989-2226

www.passeportelite.com

PHYSICAL & CHEMICAL CHARACTERISTICS

| Туре | Acrylic latex |
|-----------------------------|--|
| Exposure | Interior or exterior |
| Specular Gloss | 5° ± 2 |
| Volume Solids | 54.3% ± 2 |
| Weight Solids | 70% ± 2 |
| Vehicle Solids | 80.1% ± 2 |
| Pigment | 19.9% ± 2 |
| Dry Film Thickness | 9 mils |
| Viscosity at 77°F | 85 KU ± 5 |
| Maximum VOC | 100 g/L |
| Flash Pt °F | Non-combustible |
| Thinner | Water |
| Clean Up | Soap and water |
| Available Colours and Bases | Tintable white Accent base |
| Available Package Sizes | 3.78 L (weight per gallon: 12.7 lbs \pm 0.5 lb) |
| Drying Times | To touch: 4 hours To handle: 18 hours To recoat: 12 hours To wash: 14 days (at 70-77°F, 50% R.H.) |
| Surface Spread Rate | Smooth: 80-100 s.f./gal. Porous: 60-80 s.f./gal. (Spray application is 50% of above) |
| Tools and Equipment | Brush: Synthetic, Nylon or Polyester Roller: ³ / ₈ "-1/2" Nap Airless Spray: Not recommended Squeegee |

TECHNICAL SHEET ANTI-SLIP COATING PE700490 • PE700491

3/3

TECHNICAL SHEET ANTI-SLIP COATING PE700490 • PE700491