

TECHNICAL SHEET

STEINA END CUT SEALER

PE700881 • PE700882

DESCRIPTION

Packaging: 946 ml

STEINA End Cut Sealer weatherproofs cut ends exposing untreated wood. It prevents checking and warping and protects wood from rotting. This ready-to-use water-based product is ideal for exterior softwood, hardwood and exotic wood above-ground surfaces.

PE700881 **Natural - 610**
 PE700882 **Brown - 680**

- Water-based, non-toxic formula
- Pressure treated wood preservation
- Ready to use
- Easy to apply
- Good wood surface penetration
- For all types of hardwood and softwood
- Moisture repellent
- Anti-splitting
- Very low VOC content

TECHNICAL DATA

| | |
|-------------|--|
| pH | 7.8-8.2 |
| Solids | 33 ± 1% (by weight) |
| Viscosity | 38-40 seconds Ford cup #4 |
| Density | 0.97-0.98 kg/L |
| Drying time | Approximately 1 hour at 20°C (68°F) and 50% relative humidity |
| Coverage | Approximately 250 sq. ft. per gallon (23 sq. m. per 3.78 L) Coverage will vary depending on surface porosity and preparation. |
| VOC | 3 g/L |
| Applicators | Bristle brush, 10 mm lint-free roller or spray gun. |
| Clean up | Warm soapy water |
| Storage | Minimum temperature 5°C (41°F) Maximum temperature 35°C (95°F) PROTECT FROM FREEZING. KEEP OUT OF REACH OF CHILDREN. |
| Shelf life | At least 1 year in a well closed container |

TECHNICAL SHEET
STEINA END CUT SEALER
PE700881 • PE700882

APPLICATION CONDITIONS

Air and surface temperature should be between 12°C and 25°C (53°F and 77°F).
Relative humidity should be between 15 and 50%. Do not apply if rain is expected within 12 hours.

SURFACE PREPARATION

The product can be applied on a damp surface but not wet.

APPLICATION

Stir thoroughly. Test the product in a small, inconspicuous area. Apply generously in a single coat with a quality bristle brush, a 10 mm lint-free roller or a spray gun. Clean all equipment with hot soapy water immediately after use.

LIMITATION OF WARRANTY

The manufacturer's liability, expressed or implied, is limited to the replacement of the product. The user assumes full responsibility for use in accordance with the product data sheet. The manufacturer is not liable for any direct, indirect, consequential, economic or other damages.