



Distributions Fillion Marquis International Itée
 925 Rue Gaudette, Saint-Jean-sur-Richelieu (Québec) J3B 7S7
 Tel : 450 349-2226 • Fax : 450 349-1799 • Toll Free : 1 877 989-2226
passeportelite.com

TECHNICAL DATA SHEET
PASSEPORT ELITE INDUSTRIAL
MOISTURE VAPOR BARRIER
AND CONTAMINATED FLOOR
COATING
PE700897

DESCRIPTION

The **Passeport Elite Industrial Moisture Vapor barrier and Contaminated Floor Coating** is a 100% solid, two component epoxy coating system designed to be used as a moisture vapor barrier for contaminated concrete floors. It can be used as a primer, bonding agent as well as a top coat. It offers a long pot life while providing some fast-curing speed at ambient and low temperature conditions. It also exhibits excellent mechanical properties. This Passeport Elite product controls moisture vapor emission rates up to 25 lb. /24 hr. /1000 square feet while providing excellent mechanical properties and good chemical resistance.

PRIMARY APPLICATION

- Dry and humid treatment areas
- Commercial and industrial buildings
- Health care facilities
- Laboratories
- Surfaces where moderate mechanical and chemical resistance is needed
- Recreation centers □

ADVANTAGES

- Minimum application of 10 mils for a smooth finish or orange peel texture may appear
- Contains 100% solids, allowing for interior applications without harmful odors
- Impermeable and seamless
- Anti-slip texture that is easy to clean
- Seamless coves can be shaped using SCI-100-COVE
- Dense surface resistant to bacteria and moisture and easy to clean
- Excellent adhesive properties, allowing for application on a wide variety of substrates
- May apply several layers on itself with excellent adhesion
- Controls contamination

TECHNICAL DATA

Packaging litres / gal us	11,34 L / 3 gallons		
Color	Part A	Part B	Mix
	Upon request	Amber	Same as Part A
Recommended Thickness			
	Primer	16 mils / 100 ft ² us gal	
	Finish Coat	16 mils / 100 ft ² us gal	
Shelf Life	12 months in original unopened factory sealed containers. Keep away from extreme cold, heat, or moisture. Keep out of direct sunlight and away from fire hazards.		
Mix Ratio, by volume	A : B = 2 : 1		
Mix Ratio, by weight	100/46 (Clear) or 100/44 (Colored)		

**Please note, that the indicated mileage is calculated for flat surfaces.
 A porous or imperfect surface will require more material in order to cover the same surface area.**

Pot Life (150 g)	50 - 60 minutes 25°C		
VOC (g/litre)	30		
Specific Gravity	Part A	Part B	Mix
	Clear	1.14	1.01
	Colors	1.15-1.20	1.01
Solids Content, by weight	100%		
Thinner Recommended	Xylene		



Distributions Fillion Marquis International Itée
 925 Rue Gaudette, Saint-Jean-sur-Richelieu (Québec) J3B 7S7
 Tel : 450 349-2226 • Fax : 450 349-1799 • Toll Free : 1 877 989-2226
passeportelite.com

TECHNICAL DATA SHEET
 PASSEPORT ELITE INDUSTRIAL
 MOISTURE VAPOR BARRIER
 AND CONTAMINATED FLOOR
 COATING
 PE700897

Waiting Time/ Overcoat Ability	Substrate Temperature	Minimum	Maximum
	10 °C / 50°F	16 hours	48 hours
	20 °C / 68°F	8 hours	24 hours
	30 °C / 86°F	6 hours	24 hours

Curing details			
Substrate Temperature	Foot Traffic	Light Traffic	Full Cure
10 °C / 50°F	30 hours	5 days	10 days
20 °C / 68°F	24 hours	3 days	7 days
30 °C / 86°F	16 hours	2 days	5 days

PROPERTIES @ 23°C (73°F) and 50% R.H.

Bond Resistance (psi), ASTM D4541	268 (substrate ruptures)		
Permeability (%) ASTM D570	0.3		
Hardness (Shore D), ASTM D2240	85 - 90		
Tensile Strength (psi), ASTM D638	5500		
Compressive Strength (psi MPa), ASTM D695	6800		
Elongation %, ASTM D638	6,70%		
Abrasive resistance, ASTM D4060 (CS17 / 1000 cycles / 1000 g)	0.10g		
Viscosity (cps)	Part A	Part B	Mix
Clear	2500-2700	20000-23000	6500-7000
Colors	2700-3200	20000-23000	7000-7500
Fire Rating CAN/ULC S102	Estimated on similar coating		
	Flame Spread 5		
	Smoke developed 94		

**Note: Times and data mentioned are based on laboratory conditions.
 Field results may vary and will be affected by changing ambient conditions, especially changes in temperature and relative humidity.*

SURFACE PREPARATION

The surface to be coated must be well primed. Remove dust, laitance, grease, oils, dirt, impregnating agents, waxes, foreign matter, any previous coatings, and disintegrated substances by mechanical means such as shot-blasting (BLASTRAC) or any other approved method to obtain an ICRI-CSP 3-4 profile. The compressive strength of the concrete must be at least 25 MPa (3625 lbs/in²) after 28 days and the tensile strength at least 1.5 MPa (218 lbs/in²).

TECHNICAL DATA SHEET
PASSEPORT ELITE INDUSTRIAL
MOISTURE VAPOR BARRIER
AND CONTAMINATED FLOOR
COATING
PE700897

MIXING

The products must be conditioned at a temperature between 18°C (65°F) and 30°C (86°F).

Pre-mixed color or clear (A)

Mix the resin part (A) perfectly before pouring the hardener (part B) according to the indicated mixing ratio. Depending on product amount and size of mixing equipment, mix for 1 to 3 minutes at low speed (300 to 450 rpm). During mixing, scrape the walls and bottom of the container at least once with a trowel to obtain a homogeneous mixture. As the pot life is limited, prepare amount of desired product as required in order to avoid any loss.

Part (A) when adding color pod

Incorporate a full colored container into the clear part (A), and then thoroughly mix until the color is uniform (one colored container pod per part A gallon) before pouring in the hardener (part B) according to the indicated mixing ratio. Depending on product amount and size of mixing equipment, mix for 1 to 3 minutes at low speed (300 to 450 rpm). During mixing, scrape the walls and bottom of the container at least once with a trowel to obtain a homogeneous mixture. As the pot life is limited, prepare amount of desired product as required in order to avoid any loss.

APPLICATION

1st coat (16 mils)

Apply the first coat using a rubber squeegee and pass a roller to obtain a uniform coating.

2nd coat (16 mils)

Apply the second coat using a rubber squeegee and pass a roller to obtain a uniform coating. Then pass a textured roller to obtain the uniform texture desired.

CLEANING

Clean all application equipment with the recommended cleaner (Xylene). Once the product has hardened, it can only be removed by mechanical means. In case of skin contact, wash thoroughly with warm soapy water.

RESTRICTIONS

- Do not apply at temperatures below 10°C / 50°F or above 30°C / 86°F
- The relative humidity of the surrounding work environment during the application of the coating and throughout the curing process should not exceed 85%
- Substrate temperature must be 3°C (5.5°F) above dew point measured
- Humidity content of substrate must be <4% when coating is applied
- Do not apply on porous surfaces where a transfer of humidity may occur during the application
- The application of this coating on an interior or exterior substrate without a moisture barrier is at risk of detachment (by hydrostatic pressure).
- Protect the coating from all sources of moisture for a period of 48 hours
- Surface may discolor in areas exposed to regular ultraviolet light



Distributions Fillion Marquis International Itée

925 Rue Gaudette, Saint-Jean-sur-Richelieu (Québec) J3B 7S7

Tel : 450 349-2226 • Fax : 450 349-1799 • Toll Free : 1 877 989-2226

passeportelite.com

TECHNICAL DATA SHEET
PASSEPORT ELITE INDUSTRIAL
MOISTURE VAPOR BARRIER
AND CONTAMINATED FLOOR
COATING
PE700897

HEALTH AND SAFETY

In case of skin contact, wash with water and soap. In case of eye contact, immediately rinse with water for at least 15 minutes. Consult a physician. For respiratory irritations, move affected person outdoors to fresh air. Remove contaminated clothes and wash before reuse.

Components A and B contain toxic ingredients. Prolonged contact of this product with the skin is susceptible to provoke irritation. Avoid eye contact. Contact with product may cause severe burns. Avoid breathing vapors released from this product. This product is a strong sensitizer. Wear safety glasses and chemical resistant gloves. A breathing apparatus filtering organic vapors approved by the NIOSH/MSHA is recommended. Always work in a properly ventilated area.

Consult the material safety data sheet for further information.

IMPORTANT NOTICE

All statements, recommendations and technical information contained in this document are accurate to the best knowledge of Passeport Elite. The data relates only to the specific material designated herein. It may not be valid if used in combination with any other materials. It is the users' responsibility to verify suitability of this information for their own particular use, and to test this product before use. Passeport Elite assumes no legal responsibility for use upon these data. Passeport Elite assumes no legal responsibility for any direct, indirect, consequential, economic, or any other damage except to replace the product or refund the purchase price as set out in the purchase agreement.