



Distributions Fillion Marquis International Itée

100-420, industriel blvd., Saint-Jean-sur-Richelieu (Québec) J3B 4S6
Tel. : 450 349-2226 • Fax : 450 349-1799 • Toll Free : 1 877 989-2226
passeportelite.com

TECHNICAL DATA SHEET
METALLIC COLOURANT FOR
EPOXY AND POLYASPARTIC
PE700935 TO PE700943
PE700242 TO PE700245

DESCRIPTION

Passeport Élite Metallic Colourants for Epoxy and Polyaspartic are metallic universels pigment dispersions formulated to color coating systems. They are compatible with epoxies, polyaspartics and high-solids polyureas. This system complies with Canadian Food Inspection Agency (C.F.I.A.) standards.

Packaging - 500ml

- Silver - 101 - PE700935
- Charcoal - 124 - PE700936
- Moka - 128 - PE700937
- Hot Chocolate - 148 - PE700938
- Copper - 106 - PE700939
- Aqua - 143 - PE700940
- Misty Blue - 112 - PE700941
- Violet - 116 - PE700942
- Olive - 113 - PE700943

Packaging - 1L

- Silver - 101 - PE700242
- Charcoal - 124 - PE700243
- Moka - 128 - PE700244
- Hot Chocolate - 148 - PE700245

ADVANTAGES

- High viscosity
- High coverage
- Very low VOC content (VOC = 0.070 g/L)

TECHNICAL DATA

Packaging	500 ml or 1L
Shelf life	12 months in original unopened factory sealed containers. Keep away from extreme cold, heat, or moisture. Keep out of direct sunlight and away from fire hazards.
Mix Ratio by volume	500ml / 3,78L of Part A
Specific Gravity (25°C)	1.45-1.55
VOC	0,070 g/L

STORAGE

All **Passeport Élite epoxy and polyaspartic metallic colorants** should be stored in dry places at temperatures between 12-28 °C. Do not expose them to freezing or excessive temperatures.

MIXING

Mix **Passport Elite metallic epoxy and polyaspartic colorant** in 500ml for 2 minutes with each Part A (3.78L) of the product you want to add this colorant before adding Part B. Once the Part A mixture is homogeneous, pour in Part B of the product, respecting its volume ratio.



Distributions Fillion Marquis International Itée

100-420, industriel blvd., Saint-Jean-sur-Richelieu (Québec) J3B 4S6
Tel. : 450 349-2226 • Fax : 450 349-1799 • Toll Free : 1 877 989-2226
passeportelite.com

TECHNICAL DATA SHEET
METALLIC COLOURANT FOR
EPOXY AND POLYASPARTIC
PE700935 TO PE700943
PE700242 TO PE700245

CLEANING

Clean with Xylene.
In case of skin contact, wash thoroughly with warm water while soaping up.

HEALTH AND SAFETY

In case of skin contact, wash with water and soap. In case of eye contact, immediately rinse with water for at least 15 minutes. Consult a physician. For respiratory irritations, move affected person outdoors to fresh air. Remove contaminated clothes and wash before reuse.

Components A and B contain toxic ingredients. Prolonged contact of this product with the skin is susceptible to provoke irritation. Avoid eye contact. Contact with product may cause severe burns. Avoid breathing vapors released from this product. This product is a strong sensitizer. Wear safety glasses and chemical resistant gloves. A breathing apparatus filtering organic vapors approved by the NIOSH/MSHA is recommended. Always work in a properly ventilated area.

Consult the material safety data sheet for further information.

IMPORTANT NOTICE

All statements, recommendations and technical information contained in this document are accurate to the best knowledge of Passeport Elite. The data relates only to the specific material designated herein. It may not be valid if used in combination with any other materials. It is the users' responsibility to verify suitability of this information for their own particular use, and to test this product before use. Passeport Elite assumes no legal responsibility for use upon these data. Passeport Elite assumes no legal responsibility for any direct, indirect, consequential, economic, or any other damage except to replace the product or refund the purchase price as set out in the purchase agreement.